

# Strato

Water based. Environmentally friendly. Low in Odour.



1

**Strato 101**  
Wood adhesive binder  
with sanding dust

approx. 30 mins.



**Strato 101**  
Wood adhesive binder  
with sanding dust

approx. 30 mins.



2

**Strato 200**  
Wood floor sealer  
reduces side bonding

approx. 60 mins.



**Strato one-comp. or  
two-comp.finish**

approx. 6 hrs.



3

**Strato one-comp. or  
two-comp.finish**

approx. 6 hrs.



**Strato one-comp. or  
two-comp.finish**

approx. 6 hrs.



4

**Strato one-comp. or  
two-comp.finish**

approx. 6 hrs.

**Strato one-comp. or  
two-comp.finish**

approx. 6 hrs.

**Final hardness: approx. 7 days**



For maintenance we recommend  
**euku-wax** anti-slip or **euku-mattwax**

# 1 HS Öl + two-comp.Strato

It looks like oiled, but it is easy to maintain as it is sealed.



1

**Strato 101**  
Wood adhesive binder  
with sanding dust

approx. 30 mins.



2

**euku-öl 1 HS**  
high solid oil used as  
primer

within 15 mins.



approx. 12-24 hrs.



3

**Strato two-comp.**

approx. 6 hrs.



4

**Strato two-comp.**

approx. 6 hrs.

**Final hardness: approx. 7 days**



For maintenance we recommend  
**euku-wax** anti-slip or **euku-mattwax**

# euku-öl HS high solid

The natural looking surface treatment in one day.



1

**H 99 / H 99 S**  
Wood adhesive binder  
with sanding dust

approx. 20 mins.



or



**Strato 101**  
Wood adhesive binder  
with sanding dust

approx. 30 mins.



2

**euku-öl 1 HS**  
High solid oil for matt  
surface

within 15 mins.



**euku-öl 2Plus HS**  
Oiling and waxing in one  
procedure

within 15 mins.



3

**euku-pflegeöl**  
for final surface treatment

within 15 mins.



approx. 24 hrs.

**euku-refresher**  
for final surface treatment

within 15 mins.



approx. 24 hrs.

and finish with eukula polishing cloth  
euku-öl 1 HS + euku-pflegeöl = matt  
euku-öl 2 Plus HS + euku-refresher = satin

**Final hardness: approx. 8 days**

For maintenance we recommend the  
**euku-pflege-emulsion**

# UA

One component alkyd urethane coating (oil-modified) for wood floors. Minimizes side bonding. Suitable for underfloor heating, boards and block boards.



## 1

**H 99 / H 99 S**  
Wood adhesive binder  
with sanding dust

approx. 20 mins.



**H 99 / H 99 S**  
Wood adhesive binder  
with sanding dust

approx. 20 mins.



## 2

**G 200**  
Universal wood primer

approx. 30 mins.



**UA 510 / 511 / 512**  
Coating + 10-20%  
**V 28 UA**-thinners

approx. 6 hrs.



## 3

**UA 510 / 511 / 512**  
Coating

approx. 12 hrs.



**UA 510 / 511 / 512**  
Coating

approx. 12 hrs.



## 4

**UA 510 / 511 / 512**  
Coating

approx. 24 hrs.

**UA 510 / 511 / 512**  
Coating

approx. 24 hrs.

**Final hardness: approx. 8 days**



For maintenance we recommend  
**euku-wax** anti-slip

# Non-Stop Trowel Application

The 1 day quality coating for residential floors.



## 1

**H 99 / H 99 S**  
Wood adhesive binder  
with sanding dust

approx. 20 mins.



**H 99 / H 99 S**  
Wood adhesive binder  
with sanding dust

approx. 20 mins.



## 2

**G 240 or G 280**  
Trowel Primer

approx. 10 mins.



**G 280**  
Trowel Primer

approx. 10 mins.



## 3

**G 240 or G 280**  
Trowel Primer

approx. 40 mins.



**G 280**  
Trowel Primer

approx. 40 mins.



## 4

**UA 510 / 511 / 512**  
one-comp. UA finish

approx. 24 hrs.



**PU 551/  
PU 550 Hardener**  
two-comp. PU finish

approx. 12 hrs.

**Final hardness: approx. 8 days**

For maintenance we recommend  
**euku-wax** anti-slip

# eukula®

the best in wood floor protection

## Application Guidelines

Condensed information.  
Please follow the technical data sheets.

eukula Sealing System  
Step by Step



**eukula GmbH**  
Am Bahnhof 6, Döggingen  
78199 Bräunlingen  
DEUTSCHLAND  
Phone +49 77 07 / 151-206  
or +49 77 07 / 151-248  
Fax +49 77 07 / 151-245  
eMail: [vertrieb@eukula.de](mailto:vertrieb@eukula.de)  
Internet: [www.eukula.de](http://www.eukula.de)