



A surface like oiled but easy to maintain because it is sealed with a two-component sealer

Close the gaps with our wood adhesive binder, Strato 101, in order to avoid any darkening of the gaps.

After approx. 30 min. the floor has to be sanded and oiled with the euku-öl 1 HS to be used as a primer. This is also possible with the euku-öl 1 HS tinted with the euku-öl color.

The next day you can finish the floor without intermediate sanding with our two-component water based finishes (Strato 461/462/463 incl. Strato 460 hardener).

And please put on the second coat after a drying time of approx. 6 h, but now, of course, with intermediate sanding.

The result will convince you and your customers.

It looks like oiled, but it is easy to maintain because it is sealed with our top two-component finish.