



KEEP IT SIMPLE SHORT

Quick Sealing of Staircases with Strato 331 satin / 332 matt

How to treat raw steps with Strato 331 satin / 332 matt

1 x Strato 331/332	30 – 40 Min. Drying time for spray application
	4h* Drying time for roller application

Intermediate sanding

1 x Strato 331/332	30 – 40 Min. Drying time for spray application
	4h* Drying time for roller application

* Under optimal conditions, i.e. at 23 °C and a humidity of 50% the Strato finish is dry after approx. 4 hours and can be walked on and sanded.

Final hardness for spray application: 48 h.

Final hardness for roller application with two coats: 3 days!

Maintenance with euku-wax according to DIN 18032.

In case of airless spraying diluting is not necessary (nozzle Ø 0,28 or 0,33 mm), in case of pneumatic spraying the material can be diluted by adding up to 5% water!

How to treat raw steps with euku-naturöl

1 x euku-naturöl	15 Min. penetration time
	Polish with a beige pad or
	a lint-free cloth. Final hardness is reached after approx. 12 h.

Maintenance with euku-pflege-emulsion.

Apply the euku-naturöl with a cloth or in case of bigger steps with trowel. Remove surplus with a cloth and buffer the surface once again.

The result:

Your staircase is protected with a sealed as well as an oiled open-pore treatment.

In case of renovation remove the old coating completely to get an even surface