

Technical Data Sheet

G 200

Roller Primer, solvent based, for UA, PU, S-sealers

- ♦ quick drying
- ♦ suitable for exotic woods
- ♦ for light coloured sealers

Substrate:

Wood floors in a dry, oil, wax and dust free condition.

Application:

Use a roller.

Ensure the room and floor temperature is at least +10°C. Avoid draughts and direct sunlight.

No intermediate sanding!

Application

Tool

Drying Time

Coating:
1 x G 200



approx.
30 - 40 Min.

Afterwards further coating with eukula PU, UA or S-sealers.

Drying:

The drying times are approximate, depending on the room and floor temperature as well as the air humidity.

Consumption:

Approx. 100 ml/sqm.

Cleaning of Tools:

Immediately after use with Diluting Agent for Cleaning V 29.

Storage:

Store in cool and dry condition in their original container for up to 18 months.

Hazardous Goods Marking:

GefStoffV: F – Highly flammable, Xi – irritant
contains ethyl acetate 2-Propanol

VbF: Class A I

ADR-RID: Class 3

UN-Nr.: 1866

Giscode: G 3

R Terms: 11 Highly flammable
36/38 Irritating to eyes and skin
52/53 Harmful to aquatic organisms, may cause long-term adverse effects in the aquatic environment.
67 Vapours may cause drowsiness and dizziness.

S Terms: 16 Keep away from sources of ignition – No smoking.
23 Do not breathe vapour.
26 In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
38 In case of insufficient ventilation, wear suitable respiratory equipment.
51 Use only in well-ventilated areas.
61 Avoid release to the environment. Refer to special instructions/safety data sheets.

Do not leave any house plants, aquariums or food in the room.

Disposal:

The material should not be allowed to enter water courses. Not set material should be treated as special waste.

Further information see our material safety data sheet