

Technical Data Sheet

G 280

Trowel Primer, solvent based (Non-Stop-Trowel-Application)

- ◆ for PU, UA and S Sealers
- ◆ quick drying
- ◆ easy to apply

Substrate:

Wood floors, except for highly absorbing wood, in a dry, oil, wax and dust free condition.

Application:

Use a stainless steel trowel. Trowel twice criss-cross. No intermediate sanding! Trowel traces can be equalized with dilution Agent V 29.

Ensure the room and floor temperature is at least +10°C. Avoid draughts and direct sunlight.

Cleaning of Tools:

Immediately after use with Diluting Agent for Cleaning V 29.

Storage:

Store in cool and dry condition in their original container for up to 18 months.

Hazardous Goods Marking:

GefStoffV: F – Highly flammable, contains acetone
Xi - irritant

VbF: A I

ADR-RID: 3

UN-Nr.: 1866

Giscode: G 2

R Terms: 11 Highly flammable
36 Irritating to eyes
66 Repeated exposure may cause skin dryness or cracking.
67 Vapours may cause drowsiness and dizziness.



eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Drucknummer: 128 Stand: 03 2010 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.

Application	Tools	Drying Time
<u>Coating:</u> 1 x G 280		approx. 10 min.
1 x G 280		approx. 40 min.

Afterwards further coating with eukula PU, UA or S-sealers.

Drying:

The drying times are approximate, depending on the room and floor temperature as well as the air humidity.

Consumption:

Approx. 30 - 40 ml/sqm. per coat.

- S Terms:
- 16 Keep away from sources of ignition – No smoking.
 - 23 Do not breathe vapour.
 - 24 Avoid contact with skin.
 - 26 In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
 - 38 In case of insufficient ventilation, wear suitable respiratory equipment.
 - 51 Use only in well-ventilated areas.

- P Terms:
- 99 Contains reaction product: bisphenol A-(epichlorhydrin); epoxy resin. May produce an allergic reaction.

Do not leave any house plants, aquariums or food in the room.

Disposal:

The material should not be allowed to enter water courses. Not set material should be treated as special waste.

Further information see our material safety data sheet