

Technical Data Sheet

UA 490 gloss

UA 491 satin

1-C. Sealer, solvent based for sport floors

- ◆ anti-slip for sport floors
- ◆ suitable for underfloor heating
- ◆ reduce lateral bonding

Substrate:

Wood paving, floor boards and floating wood floors or soft-, hard- and exotic wood in a dry, oil, wax and dust free condition.

Application:

Use a roller. The material is also for airless spraying. By using a pneumatic spray the finish should be diluted with V 28. Shake well before use. Room and floor temperature should be min. +10°C. Draughts and direct sun light should be avoided. During application, to ensure a uniformed and even degree of gloss, use either only material of the same batch number or mix materials with different batch number together.

When using on soft woods, such as pine, fir or spruce, it is possible that resin discharge may occur which will have the effect of prolonging drying and will impair the finished look.

Diluting Agent:

UA-Dilution V 28.


Application

Tool

Drying Time

Coating:

1 x UA 490
+10 – 20 %
Dilution V 28




approx. 8 h

Intermediate

Sanding:

If necessary apply
eukula UA 1-C Line Paint approx. 16 h

1 x UA 490




approx. 16 h

Intermediate

Sanding:

1 x UA 490/491



approx. 24 h

Final Hardness: after approx. 8 – 10 days.

After final hardness maintain the floor with euku-wax anti-slip.

Drying:

The drying times are approximate, depending on the room and floor temperature as well as the air humidity.

Consumption:

Approx. 100 - 120 ml/sqm. per coat.

Cleaning of Tools:

Immediately after use with UA Dilution V 28 or Washing Dilution V 29.



eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Stand: 05 2010 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.

Storage:

Store in cool and dry condition in their original container for up to 12 months.

Hazardous Goods Marking:

GefStoffV: not applicable

VbF: A II

ADR-RID: 3

UN-Nr.: 1866

Giscode: KH 1

R Terms: 10 Flammable
66 Repeated exposure may cause skin dryness or cracking.

S Terms: 23 Do not breathe vapour.
24 Avoid contact with skin
38 In case of insufficient ventilation, wear suitable respiratory equipment.
51 Use only in well-ventilated areas.

P Terms: 99 Contains 2-butanone oxime, fatty acid, C6-19 branched, cobalt(2+)salts, may produce an allergic reaction.

Do not leave any flowers, aquariums or food in the room.

Warning – Danger of Self-Ignition:

Application cloth, rags, fleece, sanding dust etc. saturated with UA sealer, must be sealed off air tight in a metal box or soaked in water and be disposed of without risk or fire.

Disposal:

Do not dispose of in water courses. Dried material should be disposed of in appropriate facility.

Maintenance:

Protect your floor with the appropriate maintenance:

For cleaning, put euku-clean in the wiping water and for maintenance use euku-wax anti-slip for all gloss and satin sealed floors.

Further information see our material safety data sheet.

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Stand: 05 2010 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.