

UA 510 gloss UA 511 satin/UA 512 matt 1-C. Sealer, solvent based

Technical Data Sheet

- ♦ reduce lateral bonding, suitable for under-floor heating.
- ♦ high mechanical and chemical resistance
- ♦ lead free and low in odour

Substrate:

Wood paving, floor boards and floating wood floors or soft-, hard- and exotic wood in a dry, oil, wax and dust free condition.

Application:

Use a roller. The material is also for airless spraying. By using a pneumatic spray the finish should be diluted with V 28. Shake well before use. Room and floor temperature should be min. +15°C. Draughts and direct sun light should be avoided.

When using on soft woods, such as pine, fir or spruce, it is possible that resin discharge may occur which will have the effect of prolonging drying and will impair the finished look.

Diluting Agent:

UA-Dilution V 28.

Application

Tool

Drying Time

Coating:

a) Living areas:

2 x G 240 or
G 280



approx.
30-40 min.

1 x UA 510 or
UA 511/UA 512



approx. 12 h

b) exotic woods or waxed old floors:

1 x G 200



approx.
30 – 40 min.

1 x UA 510



approx. 12 h

Intermediate Sanding:

1 x UA 510 or
UA 511/UA 512



approx. 12 h

c) floors exposed to high stress with underfloor heating:

1 x UA 510 +
10 – 20% V 28



approx. 6 h

Intermediate Sanding:

1 x UA 510



approx. 12 h

Intermediate Sanding:

1 x UA 510 or
UA 511/UA 512



approx. 12 h

Final Hardness: after approx. 8 – 10 days

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Stand: 03 2010 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.

Drying:

The drying times are approximate, depending on the room and floor temperature as well as the air humidity. In cases of low temperatures and high air humidity, the drying process may be retarded.

Consumption:

Approx. 100 - 120 ml/sqm per coat.

Cleaning of Tools:

Immediately after use with UA Dilution V 28 or Washing Dilution V 29.

Storage:

Store in cool and dry condition in their original container up to 12 months.

Hazardous Goods Marking:

GefStoffV: not applicable

VbF: A II

ADR-RID: 3

UN-Nr.: 1866

Giscode: KH 1

R Terms: 10 Flammable

S Terms: 51 Use only in well-ventilated areas
23 Do not breathe vapour
38 In case of insufficient ventilation,
wear suitable respiratory equipment.

P Terms: 99 Contains 2-butanone oxime, fatty
Acid, C6-19 branched, cobalt (2+) salts.
May produce an allergic reaction.

Do not leave any flowers, aquariums or food in the room.

Warning – Danger of Self-Ignition:

Application cloth, rags, fleece, sanding dust etc. saturated with UA sealer, must be sealed off air tight in a metal box or soaked in water and be disposed of without risk or fire.

Disposal:

Do not dispose of in water courses. Dried material should be disposed of in appropriate facility.

Maintenance:

Protect your floor with the appropriate maintenance: For cleaning, put euku-clean in the wiping water and for maintenance use euku-wax anti-slip for all gloss and satin sealed floors and the euku-mattwax for all matt and extra matt sealed floors.

Further information see our material safety data sheet.

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Stand: 03 2010 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.