

## Technical Data Sheet

### euku-exterior Oil Pro teak

Oil for exterior application on any kind of wood

Based on vegetable oils

- ◆ UV protection
- ◆ high solid content
- ◆ quick drying

#### Substrate:

Wood in dry, oil, wax and dust-free condition. Sand coatings before application. We recommend to treat soiled and grey floors with our euku-conditioner.

#### Application:

Shake well before application! The floor temperature should be min. + 15°C.

Application	Tool	Drying Time
<u>Coating:</u> 1 x euku-exterior Oil Pro teak	Brush/Cloth	approx. 12h

Any excess material should be removed within 15 min.

If necessary you can repeat the procedure after approx. 12 h.

Final hardness after approx. 48 h

#### Drying:

The drying times are approximate, depending on the room and floor temperatures as well as the air humidity.

#### Consumption:

approx. 80 ml/sqm per coat

#### Cleaning of Tools:

Immediately after use with Washing Dilution V 29.

#### Storage:

Store in cool and dry condition in their original container, up to 12 months.

Further information see our material safety data sheet.

#### Hazardous Goods Marking

GefStoffV: not applicable

VbF: not applicable

ADR-RID: not applicable

UN-Nr.: not applicable

Giscode: Ö 60

R-Sätze: not applicable

S-Sätze: 23 Do not breathe vapour.

38 In case of insufficient ventilation,  
wear suitable respiratory equipment

#### Disposal:

Do not dispose of in water courses. Dried material should be disposed of in appropriate facility.

#### Warning – Danger of Self-Ignition:

Application cloth, rags, fleece, sanding dust etc. saturated with oil or refresher, must be sealed off air tight in a metal box or soaked in water and be disposed of without risk of fire.

#### Maintenance:

Refresh once or twice a year with euku-exterior Oil teak.

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: [vertrieb@eukula.de](mailto:vertrieb@eukula.de) Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Stand: 03 2011 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.