

Technical Data Sheet

euku-exterior Oil basic

Oil for refreshing all kinds of wood for exterior application

Based on vegetable oils

- ◆ UV protection
- ◆ high solid content
- ◆ quick drying

Further information see our material safety data sheet.

Substrate:

All kinds of wood in dry, oil, wax and dust-free condition.

Hazardous Goods Marking:

GefStoffV: not applicable

VbF: A III

ADR-RID: not applicable

UN-Nr.: not applicable

Giscode: Ö 60

R-phrases:52/53 Harmful to aquatic organisms, may cause long-term adverse effects in the aquatic environment.

66 Repeated exposure may cause skin dryness or cracking.

S-phrases:24 Avoid contact with skin.

38 In case of insufficient ventilation, wear suitable respiratory equipment.

61 Avoid release to the environment. Refer to special instructions/safety data sheet.

23 Do not breathe vapour.

P-phrases:99 Contains 2-butanone oxime, Cobaltbis (2-ethylhexanoat), 4,5-Dichlor-2-octyl-2H-isothiazol-3-on. May produce an allergic reaction.

Application:

Shake well before application! The floor temperature should be min. + 15°C.

Application	Tool	Drying Time
<u>Coating:</u> 1 x euku-exterior Oil basic	Brush/Cloth	approx. 12h

Any excess material should be removed within 15 min.

If necessary you can repeat the procedure after approx. 12 h.

Final hardness after approx. 48 h

Drying:

The drying times are approximate, depending on temperature and climate.

Consumption:

approx. 60 ml/sqm per coat on flat surfaces.

Cleaning of Tools:

Immediately after use with Washing Dilution V 29.

Storage:

Store in cool and dry condition in their original container, up to 18 months.

Disposal:

Do not dispose of in water courses. Dried material should be disposed of in appropriate facility.

Warning – Danger of Self-Ignition:

Application cloth, rags, fleece, sanding dust etc. saturated with oil or refresher, must be sealed off air tight in a metal box or soaked in water and be disposed of without risk of fire.

Maintenance:

Refresh once or twice a year with euku-exterior Oil basic.

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Stand: 03 2011 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.