

Technical Data Sheet

euku-öl 2 plus

Hardwax Oil, based on Natural Oils and Wax

- ♦ oiling and waxing in one procedure
- ♦ even, satin surface
- ♦ suitable for underfloor heating

Application:

Coating:

1 x euku-öl 2
Plus
and buff

Tool



Drying Time

approx.
12 h

Substrate:

Soft and hardwood floors in a dry, dust and dirt free condition.

*You can enter the floor carefully after approx. 1 h.

The oiled floor must not be wet wiped within 7 days of application. Wait at least 8-10 days before cleaning or laying rugs.

Application:

The floor has to be properly sanded. Room and floor temperature should be min + 10°C. Draughts and direct sun light should be avoided. A resin discharge may sometimes occur from soft or exotic wood which might be detrimental to the look of the coating. Shake well before use. Apply it with a trowel or a soft cloth. Remove any surplus with trowel, oil removing rubber blade or cloth. Pad the wet film with a multi-purpose machine and a beige pad or a soft cloth so that an even surface is achieved. Please avoid drying of the oil before padding. Apply immediately afterwards the euku-refresher with a trowel or bigger surfaces with a T-frame, pad it immediately and put the polishing cloth around the pad and polish the surface with the multi-purpose machine.

Drying:

The drying times are approximate, depending on the room and floor temperatures as well as the air humidity.

Consumption:

Approx. 30 –50 ml/m²
1 l – approx. 30 sqm.

Cleaning of Tools:

Immediately after use with UA Dilution V 28 or Washing Dilution V 29.

Dilution:

If necessary with UA-Dilution Agent V 28.

Storage:

Store in cool and dry condition in their original container, up to 24 months.



eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Drucknummer: 325 Stand: 03 2008 1 GB Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.

Disposal:

The material should not be allowed to enter water courses. Not set material should be treated as special waste.

Contents:

Linseed oil, alkyd-resin, wax, isoalphanates and lead-free driers.

Further information see our material safety data sheet.

Warning – Danger of Self-Ignition:

Application cloth, rags, fleece, sanding dust etc. saturated with oil or refresher, must be sealed off air tight in a metal box or soaked in water and be disposed of without risk of fire.

Maintenance:

Use the euku-pflege-emulsion in the wiping water, earliest after 7 days. Please follow the maintenance instructions.

Hazardous Goods Marking:

GefstoffV: not applicable

VbF: All

ADR-RID: 3

UN-Nr.: 1866

Giscode: Ö60

R Terms: 10 Flammable

S Terms: 51 Use only in well-ventilated areas.

23 Do not breathe vapour.

38 In case of insufficient ventilation, wear suitable respiratory equipment

P Terms: 99 Contains 2-butanone oxime, fatty acid, C6-19 branched, cobalt (2+)salts. May produce an allergic reaction.

Do not leave any flowers, aquariums or food in the room.

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Drucknummer: 325 Stand: 03 2008 1 GB Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.