

Technical Data Sheet

euku-öl 2 plus HS high solid High Solid Hardwax Oil, based on Natural Oils and Wax

- ♦ oiling and waxing in one procedure
- ♦ even, satin surface
- ♦ suitable for underfloor heating

Substrate:

Soft and hardwood floors in a dry, dust and dirt free condition.

Application:

The floor has to be properly sanded. Room and floor temperature should be min + 10°C. Draughts and direct sun light should be avoided. A resin discharge may sometimes occur from soft or exotic wood which might be detrimental to the look of the coating. Shake well before use. Apply it with a trowel or a soft cloth. Remove any surplus with trowel, oil removing rubber blade or cloth. Pad the wet film with a multi-purpose machine and a beige pad or a soft cloth so that an even surface is achieved. Please avoid drying of the oil before padding. Apply immediately afterwards the euku-refresher with a trowel or bigger surfaces with a T-frame, pad it immediately and put the polishing cloth around the pad and polish the surface with the multi-purpose machine.

Dilution:

If necessary with UA-Dilution Agent V 28.

Application:

Coating:
1 x euku-öl 2
Plus HS
and buff

Tool



Drying Time

min.
30 min.

1 x euku-refresher*
and buff



approx.
12 h

*You can enter the floor carefully after approx. 1 h.

The oiled floor must not be wet wiped within 7 days of application. Wait at least 8-10 days before cleaning or laying rugs.

Drying:

The drying times are approximate, depending on the room and floor temperatures as well as the air humidity.

Consumption:

euku-öl 2 plus HS
approx. 30 ml/sqm.
1 l – approx. 30 sqm.

euku-refresher:
approx. 30 ml/m²
1 l – approx. 30
sqm.

Cleaning of Tools:

Immediately after use with UA Dilution V 28 or Washing Dilution V 29.

Storage:

Store in cool and dry condition in their original container, up to 24 months.



Disposal:

The material should not be allowed to enter water courses. Not set material should be treated as special waste.

Warning – Danger of Self-Ignition:

Application cloth, rags, fleece, sanding dust etc. saturated with oil or refresher, must be sealed off air tight in a metal box or soaked in water and be disposed of without risk of fire.

Maintenance:

Use the euku-pflege-emulsion in the wiping water, earliest after 7 days. Please follow the maintenance instructions.

Hazardous Goods Marking:

GefstoffV: not applicable

VbF: All

ADR-RID: 3

UN-Nr.: 1866

Giscode: Ö60

R Terms: 10 Flammable
52/53

Harmful to aquatic organisms, may cause long-term adverse effects in the aquatic environment

66 Repeated exposure may cause skin dryness or cracking.

S Terms: 23 Do not breathe vapour.
24 Avoid contact with skin
38 In case of insufficient ventilation, wear suitable respiratory equipment
51 Use only in well-ventilated areas.
61 Avoid release to the environment. Refer to special instructions / safety data sheet.

Special provisions concerning the labelling of certain mixtures

P Terms: 99 Contains Cobaltbis (2-ethylhexanoat). May produce an allergic reaction.

Contents:

Linseed oil, alkyd-resin, wax, isoalphanates and lead-free driers.

Further information see our material safety data sheet

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Stand: 5 2010 GB Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.

Explanatory

How to oil your floor correctly

- Please observe carefully our Technical Data Sheets.
- Regular and even sanding is the main condition to achieve a uniform surface particularly in case of colour oils. Different ways of sanding, e.g. sanding to the edge, may create light and dark margins which are even more visible in case of colour oils.
- Sanding traces because of e.g. small stones in the sanding belt appear after the oiling as stripes.
- When oiling tropical wood there might be a delay in drying due to its ingredients.
- In case of highly absorbing woods like maple, beech, cherry etc. a sufficient material quantity should be applied to achieve an even saturation of the wood. In case of lack of material the surface tends to be more susceptible to dirt and stains and to greying.
- The use of a three disc machine is recommended.
- ATTENTION: Too fine sanded wood may disturb the oil penetrating into the wood.

Please note:

- Please follow our maintenance instructions for oiled floors.
- Unsuitable cleaning and maintenance products may harm the surface.
- Oiled surfaces are open-pore and thus more sensitive regarding humidity. Remove water immediately from the oiled surface.
- Maintain oiled floors according to their use.
- For the oil/water based combination ensure good ventilation (fresh air supply) when drying.

eukula-
Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH
Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Stand: 5 2010 GB Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.