

Technical Data Sheet**euku-mattwax**

- ♦ the perfect surface protection for matt sealed wood floors

Substrate:

Matt sealed wood floors and cork.

Extra matt sealed floors, e.g. Strato 442 or Strato 462 could be slightly increased in their degree of gloss.

Application:

Shake well before use!

Use only pure!

Full treatment: Apply **euku-mattwax** pure and evenly to the clean and dust free floor by using a eukula floor mop. You can walk on the floor after a drying time of approx. 30 min.

Attention: Do not treat or apply anything during the drying time, otherwise the protection film might be destroyed.

Maintenance: Add **euku-clean** to the water (50-100 ml to 10 l water) and wipe the floor with a damp cloth.

There must always be a maintenance film. Do not use euku-mattwax in medical practices. The use of disinfectants may cause stains in the maintenance film.

Application**Tool****Drying time**Coating:

1 x euku-mattwax



approx. 30 min.

Complete drying time overnight.

Drying Time:

The drying time is approximate, depending on the room and floor temperature as well as the air humidity.

Consumption:

1 ltr. - approx. 30 sqm.
approx. 35 ml/sqm.

Cleaning of Tools:

Immediately after use with water.

Storage:

Store in cool and dry condition. The material can be stored in the original container for up to 12 months.

Protect from frost!

Hazardous Goods Markings:

GefStoffV: Not applicable

VbF: Not applicable

ADR-RID: Not applicable

UN-Nr.: Not applicable

R Terms: ---

S Terms: 1/2 Keep locked and out of reach of children.

UBA: 19590009

Contents: Details in Accordance with EC Recommendations:

Less than 5% Anionic tenside, preservative, other fillers: polymer dispersions, water based solvents, perfume oil.

Further information see our material safety data sheet

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Drucknummer: 344 Stand: 05 2009 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Drucknummer: 344 Stand: 05 2009 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.