

Technical Data Sheet**euku-pflegeöl**
Maintenance Oil

- ♦ good penetration properties
- ♦ low in odour
- ♦ rejuvenates wooden floors


Substrate:

Dry and dust-free hardwood floors, treated with euku-oil 1/euku-oil 1 HS.

Application:

Apply euku-pflegeöl thin and evenly on the clean and dry floor with a trowel, T-Frame or a cloth and let it penetrate. Remove any surplus. Pad the wet film with a multi-purpose machine and a beige pad or a soft cloth so that an even surface is achieved. Thus the floor get even more resistant to dirt and humidity. The maintained floor should not be entered within the next 12 hours.

Application	Tool	Drying Time
<u>Coating:</u> 1 x euku-pflegeöl	 	approx. 30 min.

**Drying:**

The drying times are approximate, depending on the room and floor temperature as well as the air humidity.

Consumption:

Approx. 30 ml/sqm, 1 l – approx. 30 sqm

Disposal:

The material should not be allowed to enter water courses. Not set material should be treated as special waste.

Cleaning of Tools:

Immediately after use with UA Dilution V 28 or Washing Dilution V 29.

Storage:

Store in cool and dry condition in their original container, up to 24 months.

Hazardous Goods Marking:

GefStoffV: not applicable

VbF: A II

ADR-RID: 3

UN-Nr.: 1866

Giscode: Ö 60

R Terms: 10 flammable

66 Repeated exposure may cause skin dryness or cracking

S Terms: 23 Do not breathe vapour.

24 Avoid contact with skin.

38 In case of insufficient ventilation, wear suitable respiratory equipment.

51 Use only in well-ventilated areas.

P Terms:

99 Contains 2-butanone oxime, fatty acid, C6-19 branched, cobalt (2+)-salts. May produce an allergic reaction.

Do not leave any flowers, aquariums or food in the room.

Warning – Danger of Self-Ignition:

Application cloth, rags, fleece, sanding dust etc. saturated with oil or refresher, must be sealed off air tight in a metal box or soaked in water and be disposed of without risk of fire.

Further information see our material safety data sheet.

eukula

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Drucknummer: 338 Stand: 02 2009 1 GB Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.