

Strato 110 Joint Adhesive Powder

- ◆ low shrinkage
- ◆ low in odour
- ◆ fast and easy to sand
- ◆ environmentally friendly

Available Colours:

- ◆ oak
- ◆ beech
- ◆ pine/maple/ash

Substrate:

Suitable for all types of wood in a dry, oil, wax and dust free condition.

Application:

Add approx. 70% water to achieve the working consistency. Stir well when adding the water until getting a homogeneous trowelable mass. Pot life of the mixed powder is approx. 45 to 60 min. Use a stainless steel trowel only.



Coating:

Once sanded, any Strato one or two component finishes or eukula oils and hardwax oils may be applied.

Drying:

Approx. 45 to 60 min., according to the temperature and air humidity.

Consumption:

Approx. 50 – 100 ml/m², according to the quantity and the size of the joint.

Cleaning of Tools:

Immediately after use with water.

Storage:

The material can be stored in cool and dry condition in their original containers up to 18 months. Protect from frost.

Hazardous Goods Marking:

GefstoffV: not applicable
VbF: not applicable
ADR-RID: not applicable
UN-Nr.: not applicable
Giscode: W1+
R Terms: --
S Terms: --

Disposal:

The material should not be allowed to enter water courses, dried material can be treated as normal waste.

Further information see our material safety data sheet.

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Drucknummer: 316 Stand: 11 2008 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.