

Technical Data Sheet**Strato 120 color
Color Paste**

- ◆ water based
- ◆ low in odour
- ◆ environmentally friendly

Available colors:

- ◆ white
- ◆ anthracite
- ◆ rosewood
- ◆ lime-green
- ◆ chestnut
- ◆ pearl-grey
- ◆ rose
- ◆ blue
- ◆ teak
- ◆ walnut

Zusatzmenge:

Mix in between 1 and 3 % per application with Strato 370 / 371 / 372 and 441 / 442 + Strato 440 hardener resp. Strato 461 / 462 + Strato 460 hardener.

Application:

Shake Strato 120 color well before use. Add in between 1 and 3% to the Strato Sealer depending on the requested color intensity. Shake well. Apply with the roller evenly on the raw wood (approx. 120 ml/m²). The less the additional quantity, the more beautiful the surface. Three applications with 1% Strato 120 color are better than one application with 3%!

**Recommendation:**

Tests in advance on the original substrate are recommended.

Coating:

3 x Strato Sealer and 1 - 3% Strato 120 color. Intermediate sanding after the first and the second application. We recommend an additional and final finish without Strato 120 color.

Drying time:

See Application Notes of the Strato Sealer.
Consumption: 1% - 3% per l Strato finish.

Cleaning of Tools:

Immediately after use with water, dried on material with Washing Dilution V 29.

Storage:

The material can be stored in cool and dry condition in their original containers up to 12 months.
Protect from frost

Hazardous Goods Marking:

GefStoffV: not applicable
VbF: not applicable
ADR-RID: not applicable
UN-Nr.: not applicable

Giscode: W3

R Terms: ----

S Terms: ----

Disposal:

The material should not be allowed to enter water courses. Not set material should be treated as special waste.

Further information see our material safety data sheet.

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Drucknummer: 317 Stand: 02 2009 1 GB Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig..