

euku-öl 1 HS and Strato Domicile 1K satin / matt, water based for residential areas

Technical Data Sheet

- ♦ beauty of the wood is accentuated
- ♦ looks like oiled
- ♦ easy to maintain as sealed

Substrate:

Soft and hardwood floors in a dry, dust and dirt free condition.

Application:

Room and floor temperature should be min. + 15°C. Draughts and direct sun light should be avoided.

1) Application of euku-öl 1 HS

Apply euku-öl 1 HS on the evenly sanded floor (120/150 grit) with a trowel and buffer it with a beige pad.

A resin discharge may sometimes occur from soft or exotic wood which might be detrimental to the look of the coating. The oil must be dry before sealing the next day.

The euku-öl 1 HS can be tinted as described in the Technical Data Sheet. Tests in advance are recommended. If oil comes out of the joints, buffer the floor once again. After drying overnight start sealing the floor without intermediate sanding.

2) Application of Strato Domicile satin/matt

Shake Strato Domicile satin well.
Use a roller.

Application

Oil Primer

1 x euku-öl 1 HS



Drying Times


approx. 12 h/
max. 36 h

Tinting with euku-öl color, see Technical Data Sheet.

No intermediate sanding

Sealing

1 x Strato Domicile
satin/matt



approx. 5h*
with restric-
tions

Intermediate sanding:

1 x Strato Domicile
satin/matt



approx. 5h*
with restric-
tions

Final hardness: after approx. 7 days

Drying:

The drying times are approximate, depending on the room and floor temperature as well as the air humidity.

* Under optimal conditions, i.e. at 23°C and a humidity of 50% the Strato finish is dry after approx. 5 h and can be walked on and sanded. In order to avoid any swelling, drying time overnight is recommended. Also for highly absorbing woods like beech, maple and ash etc. This is also recommended in the renovation.

Consumption:

euku-öl 1 HS:
approx. 30 ml/sqm.

Strato Domicile satin/matt:
approx. 130 ml/sqm. per coat



Cleaning of Tools:

Immediately after use.

Strato: Dried on material can be removed with water or Diluting Agent V 29.

euku-öl 1 HS: With UA Dilution V 28 or Washing Dilution V 29

Storage:

Cool and dry in its original container.

euku-öl 1 HS: min. 24 months

Strato Domicile satin/matt: min. 9/6 months

Hazardous Goods Marking:

euku-öl 1 HS

GefStoffV: not applicable

VbF: not applicable

ADR-RID: no dangerous goods < 450 l

UN-Nr.: 1866

Giscode: Ö 40

R Terms: 10 Flammable

S Terms: 23 Do not breathe vapour.

38 In case of insufficient

ventilation, wear suitable

respiratory equipment

51 Use only in well-ventilated areas.

P Terms: 99 Contains 2-butanone oxime, fatty acid, C6-19 branched, cobalt (2+)salts. May produce an allergic reaction.

Disposal:

The material should not be allowed to enter water courses. Not set material should be treated as special waste.

Warning – Danger of Self-Ignition:

Application cloth, rags, fleece, sanding dust etc. saturated with oil or refresher, must be sealed off air tight in a metal box or soaked in water and be disposed of without risk of fire.

Dangerous Goods Marking of Strato Domicile satin/matt:

GefStoffV: not applicable

VbF: not applicable

ADR-RID: not applicable

UN-Nr.: not applicable

Giscode: W 3+

R Terms: ---

S Terms: 38 In case of insufficient ventilation, wear suitable respiratory equipment.

23 Do not breathe vapour.

Disposal:

Do not dispose of in water courses. Dried material should be disposed of in appropriate facility.

Maintenance:

Protect your floor with the appropriate maintenance: For cleaning, put euku-clean in the wiping water and for maintenance use euku-wax anti-slip for all satin sealed and euku-mattwax for all matt sealed floors.

Further information see our material safety data sheet.

eukula-

Gesellschaft moderner Kunststoff- und Lackbeschichtungen mbH

Döggingen Am Bahnhof 6 D-78199 Bräunlingen Tel. +49(0)7707.151-206 und 151-248 Fax +49(0)7707.151-245 E-Mail: vertrieb@eukula.de Internet: <http://www.eukula.de>

Unsere Technischen Datenblätter sollen nach dem aktuellen Kenntnisstand beraten. Diese Hinweise befreien Sie jedoch nicht von einer eigenen Prüfung unserer Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Anwendungen. Der Verkauf unserer Produkte erfolgt nach Maßgabe unserer Geschäfts- und Lieferbedingungen.

Stand: 05 2010 Mit dieser Auflage sind alle früheren Merkblätter für dieses Produkt ungültig.

Explanatory

How to oil your floor correctly

- Please observe carefully our Technical Data Sheets.
- Regular and even sanding is the main condition to achieve a uniform surface particularly in case of colour oils. Different ways of sanding, e.g. sanding to the edge, may create light and dark margins which are even more visible in case of colour oils.
- Sanding traces because of e.g. small stones in the sanding belt appear after the oiling as stripes.
- When oiling tropical wood there might be a delay in drying due to its ingredients.
- In case of highly absorbing woods like maple, beech, cherry etc. a sufficient material quantity should be applied to achieve an even saturation of the wood. In case of lack of material the surface tends to be more susceptible to dirt and stains and to greying.
- The use of a three disc machine is recommended.
- ATTENTION: Too fine sanded wood may disturb the oil penetrating into the wood.

Please note:

- Please follow our maintenance instructions for oiled floors.
- Unsuitable cleaning and maintenance products may harm the surface.
- Oiled surfaces are open-pore and thus more sensitive regarding humidity. Remove water immediately from the oiled surface.
- Maintain oiled floors according to their use.
- For the oil/water based combination ensure good ventilation (fresh air supply) when drying.